



Rely on us.SM

dayGraphica[®] t3000

For higher standards of printability and reliability

Sleeves: Designed for Manroland Rotoman S and Lithoman S Presses

The development of the dayGraphica[®] t3000 seamless printing sleeve helped support the revolution in the design of high-speed rotary web presses. Since then, our uncompromising commitment to improved performance has made today's dayGraphica[®] t3000 sleeve the worldwide sales leader!

Extra care is taken to assure that all dayGraphica[®] t3000 sleeves arrive in your printing plant ready to run. Each one is hand packed in specially designed cartons which protect the sleeve by suspending it in air. While dayGraphica[®] t3000 sleeves are tough on press, they deserve gentle handling during unpacking and installation.

The dayGraphica[®] difference means every t3000 sleeve is backed by the largest and most technically qualified support team in the business. We always work harder to help make your press operators look good on paper!

This technology is now available for Manroland Rotoman S and Lithoman S press designs and will allow printers using these machines to benefit from years of technical expertise in this exciting area.

Advantages of dayGraphica[®] t3000

- Durable, stabilized carcass.
- Excellent smash recovery and rebound characteristics.



FlintGroup

dayGraphica® t3000

For higher standards of printability and reliability

Features	Benefits
Ground seamless surface layer.	dayGraphica® t3000's unique surface finish ensures consistent gauge and uniform web feed for top quality printing.
Unique seamless carcass construction.	The durable combination of fiber and compressible layer technologies ensures long life and excellent stability on press. Superb smash recovery for longer life - less downtime, more production.
Solvent resistant rubber surface compound.	Proven technology for heatset-web applications.

Color:	Dark Blue
Face Compound:	Nitrile Butadiene Synthetic Rubber designed for optimum transfer and dot fidelity.
Face Treatment:	Precision ground seamless surface finish.
Image Reinforcing Layer:	Synthetic fiber cord
Compressible Layer:	Carbon reinforced Nitrile Butadiene Synthetic rubber designed for optimum rebound and smash resistance.
Composite Carrier:	Fiberglass reinforced composite.

Press Type	Press Cutoff	Overall Length	Surface Rubber	Max Web	Thickness	Carrier	Rubber	Nominal load @ 0.13mm indent
Rotoman S Single Around	20.630in	42.126in	40.354in	40.157in	0.079in	0.025in	0.054in	0.295 N/in
	21.496in	59.449in	57.677in	57.480in	0.079in	0.025in	0.054in	0.295 N/in
	22.244in	39.961in	38.189in	37.992in	0.079in	0.025in	0.054in	0.295 N/in
	22.244in	59.449in	57.677in	57.480in	0.079in	0.025in	0.054in	0.295 N/in
	24.410in	59.449in	57.677in	57.480in	0.079in	0.025in	0.054in	0.295 N/in
Rotoman S Double Around	2x21.497in	113.386in	72.244in	72.047in	0.079in	0.030in	0.049in	0.327 N/in
	2x22.244in	113.386in	72.244in	72.047in	0.079in	0.030in	0.049in	0.327 N/in
Lithoman III S	35.040in	76.969in	75.197in	75in	0.079in	0.030in	0.049in	0.327 N/in
	35.040in	79.921in	78.150in	77.953in	0.079in	0.030in	0.049in	0.327 N/in
	35.433in	76.969in	75.197in	75in	0.079in	0.030in	0.049in	0.327 N/in
	40in	83.071in	81.299in	81.102in	0.079in	0.030in	0.049in	0.327 N/in

**Inks,
blankets,
chemicals
& more**

Rely on us™
to bring greater value to your pressroom.

For more information:

Flint Group
Print Media North America
14909 N. Beck Road
Plymouth, MI 48170
+1 734 781 4600
printmedia.na@flintgrp.com

www.flintgrp.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. Customers are responsible for confirming suitability of this product for their application. In no event shall Flint Group be liable for any errors, facts or opinions contained herein, or any claims by any party alleging reliance on these materials, regardless of the form of action.

Product names followed by a ® are trademarks registered by a Flint Group company.

Version 5/2015 Page 2 of 2