

Rely on us.SM

davidM[®] QL Blue

Economy in a variety of applications

Printing Blankets: Offset

davidM[®] QL Blue has been designed to meet today's demands for high performance on sheetfed applications. It's compatible with today's ever-changing pressroom chemistries and the carefully blended polymer surface gives you quick release, good ink affinity and resiliency. The precision buffed surface provides a micro-textured profile that enhances sheet release and ink transfer. This solvent-resistant compound provides a stable base which resists changes in hardness or thickness which can occur as a result of solvent attack.

Advantages of davidM[®] QL Blue

- Durable, high density carcass.
- Excellent rebound characteristics.

HEATSET.



FlintGroup

davidM[®] QL Blue

Economy in a variety of applications

Features	Benefits
Precision buffed surface.	Enhances sheet release and ink transfer. Permits much greater gauge control.
Blended polymer surface with a microcellular compressible base.	Enables blanket to have quick release, good ink affinity and resiliency.
Unique fabric construction.	Less susceptible to smashing and sinking due to over-tightening or excessive tension.
Solvent resistant surface.	Provides stable base which resists changes in hardness or thickness from high KB inks or harsh blanket washes.

Specifications:

Color: Blue

Surface: Ground – Ra 0.5µm Typical

Thickness:

1.96mm

Face Compound:

Solvent resistant rubber blend

Hardness:

62°

Average Compressibility:

0.13mm @ 1060 kPa Typical /

0.19mm @ 2060 kPa Typical

Tensile Strength:

>60 N/mm

Elongation:

<0.70% @ 10 N/mm

Ink Compatibility:

Conventional Sheetfed inks

Inks,
blankets,
chemicals
& more

Rely on us[™]
to bring greater value to your pressroom.

For more information:

Flint Group
Print Media North America
14909 N. Beck Road
Plymouth, MI 48170
+1 734 781 4600
printmedia.na@flintgrp.com

www.flintgrp.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. Customers are responsible for confirming suitability of this product for their application. In no event shall Flint Group be liable for any errors, facts or opinions contained herein, or any claims by any party alleging reliance on these materials, regardless of the form of action.

Product names followed by a [®] are trademarks registered by a Flint Group company.

Version 5/2015 Page 2 of 2