

*Rely on us.*SM



Novaflash® Silver 222 877 LOW VOC

Laser compatible one-component silver ink for non-absorbent substrates

Spot inks for sheetfed offset

Product features

- Novaflash® Silver 222 877 LOW VOC is a largely mineral oil-free, wax containing and stable one-component sheetfed offset metallic ink with almost oxidative drying for non-absorbent substrates. Furthermore, Novaflash® Silver 222 877 LOW VOC can be processed in laser printers. However, a finishing test should be made before commercial production starts.
- Novaflash® Silver 222 877 LOW VOC is ideally suited for straight-line printing on all multi-colour printing presses. The advantages of the silver are high brilliance and a strong metallic effect with very good printability.
- Due to the leafing properties of the gold pigments used, Novaflash® Silver 222 877 LOW VOC has a low rub resistance. This can be improved by the application of an adequate oil-based varnish or water-based coating.

Advantages of Novaflash® 222 877 LOW VOC

- Ready-to-print.
- Largely mineral oil-free.
- Ideally suited for non-absorbent substrates due to oxidative drying.
- Suitable for laser printers.
- Strong metallic effect.
- Very good printing performance.



FlintGroup

Novaflash® Silver 222 877 LOW VOC



		Fastness properties			Printing properties								
		Alcohol	Solvent mixture	Alkali	Half-tone printing	Gloss	Setting	Oxidative drying	Rub resistance	Rapid further processing	Suitability for gloss coated papers/board	Suitability for uncoated papers/board	Suitability for matt coated papers/board
Novaflash® Silver Ink	Product code				4	4	2	6	2	5	5	1	6
Silver 222 877 LOW VOC	VI89-BPPD	+	+	-	1 = Characteristic weakly expressed 7 = Characteristic strongly expressed								
		Fastness properties according to ISO 2836: + = Resistance provided - = Resistance not provided			The assessment of the colour properties was made under standardised printing conditions. In individual cases, under special conditions, as in printing with very high ink densities, the classification of certain properties may be different.								

Substrates

Ideally suited for non-absorbent substrates, very good suited for gloss coated papers and board, suited for matt coated paper and board.

The substrate selection has an important influence on the achievable metallic effect. Depending on the absorption and the surface conditions, the metallic effect can be reduced more or less. Optimal results are normally achieved on coated substrates, as well as non-absorbent substrates, e.g. metallised papers and different plastics.

Some substrates may look attractive, but cause strong penetration of oil and binding agents. Regarding the Novaflash® Silver 222 877 LOW VOC this could have a particularly strong impact, as the silver has a quite slow setting. The result may be a large amount of unwetted metal pigments on the print surface, which may cause drying and abrasion problems.

To achieve best possible results on a less than ideal substrate, an adequate primer can be pre-printed in a sufficient film thickness. This should be checked before commercial production starts.

Storage and shelf life

Metallic inks should be stored at temperatures of around 25°C, as high temperatures may cause oxidation which could lead to a decrease in brilliance. The tins should be kept closed whenever possible, as unnecessary opening results in oxidation.

Used ink from the duct must not be refilled into the tin. Mixed fountain solution can react with the aluminium particles of the metallic ink and create gas.

Meeting the recommended storage conditions, Novaflash® Silver 222 877 LOW VOC will remain stable for a minimum of 6 months from the date of manufacture.

Fountain solution

We recommend using Hydrofast® GS 307, dosed at 2-3% with additional 8% Isopropanol.

You are welcome to contact us for further information.

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.

Flint Group
Commercial, Publication & Sheetfed Inks
Sieglestrasse 25
70469 Stuttgart, Deutschland

T +49 711 98 16-0
F +49 711 98 16-700
sheetfed@flintgrp.com
www.flintgrp.com

Product names followed by ® are trademarks registered by Flint Group (represented by Flint Group US LLC or Flint Group Germany GmbH).

Novaflash® Silver 222 877 LOW VOC

Additives

To improve drying, 3-5% drying paste Novaspot® 3107 may be added. However, this should be introduced immediately before commercial production starts, because the longer the resting time the greater the chance of oxidation and the more the brilliance will suffer.
If the substrate requires the tack to be reduced, up to 3% printing oil L may be added.

Exceptions

Not for use for food packages without functional barrier.

Special Notes Print finishing

Within the print finishing, attention must be paid to the fact that metallic inks have restricted intermediate adhesion to varnish systems and other components. This is caused by the leafing characteristics of the metallic inks, which means that the metallic particles in combination with the fountain solution travel to the surface of the printed ink film. Due to a special varnish formulation, Novaflash® Silver 222 877 LOW VOC has improved intermediate adhesion properties for following water-based varnishing. To further improve the intermediate adhesion, 15-20 % silver varnish 4893 BIO may be added.

With finishing methods such as sealing and laminating the same additives in the mentioned dosages can be used. The finishing process must first be coordinated with the finishing company.

Important for a successful finishing is the drying status of the ink. Please note, that the time until the ink is completely dried depends upon various factors e.g. substrate and printing conditions (water feed). To evaluate the point at which finishing can be started, measuring the surface tension can be helpful. The surface tension should not be less than 35 mN/m.

In many cases it is recommended to use a primer e.g. Novaset® 4510/40 Offline-Primer from Flint Group. In any case a finishing test should be made before commercial production starts.

Any kind of finishing causes a reduction of the metallic effect.

Resistance Characteristics

In general metallic inks do not have alkali fastness, but they can actually be varnished with a suitable water-based coating. For overprint varnishing, we recommend Novaset® Gloss Coating 4216/40.

You are welcome to contact us for further information.

Flint Group
Commercial, Publication & Sheetfed Inks
Sieglestrasse 25
70469 Stuttgart, Deutschland

T +49 711 98 16-0
F +49 711 98 16-700
sheetfed@flintgrp.com
www.flintgrp.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.

Product names followed by ® are trademarks registered by Flint Group (represented by Flint Group US LLC or Flint Group Germany GmbH).

Novaflash® Silver 222 877 LOW VOC

Printability

Environmental influences in the print room are of major importance. The temperature and air humidity can influence the ink balance and thus the printability.

Ideally, systems for the control of air humidity and temperature should be installed in the area around the printing press. The printing press itself should not be exposed to direct sun light.

The pH-value of the fountain solution must be in a neutral range in order not to reduce the brilliance and drying. A pH-value around 5.5 is recommended. An addition of up to 8% Isopropanol has a positive effect on drying and printability.

Metallic inks can be printed wet-on-wet with other inks: the tack of the following inks should be lower, and the ink should not be high-gloss. The metallic ink should be printed in the 1st unit, the following overprint ink should be printed – if possible – in the last printing unit. As overprint Black we recommend Novavit® Black 133 RTW, respectively the Novaplast® Process Black for non-absorbent substrates.

More products. Streamlined access. Greater results.

Flint Group offers a uniquely powerful combination of products, services and expertise; giving you access to the industry's broadest range of pressroom products.

Inks & Coatings. Pressroom Chemicals. Blankets. Sleeves. Consumables.

Rely on us for consistency, reliability and customer focus. Our aim is to make it easier for you to achieve your business goals. With Flint Group products in your pressroom, you can run your business with confidence and peace of mind.

You are welcome to contact us for further information.

Flint Group
Commercial, Publication & Sheetfed Inks
Sieglestrasse 25
70469 Stuttgart, Deutschland

T +49 711 98 16-0
F +49 711 98 16-700
sheetfed@flintgrp.com
www.flintgrp.com

The aim of our technical documents is to inform and advise our customers. The information provided herein is correct to the best of Flint Group's knowledge. No liability for any errors, facts or opinions is accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.

Product names followed by ® are trademarks registered by Flint Group (represented by Flint Group US LLC or Flint Group Germany GmbH).